



# AGRIMIX™

## The solution for your agricultural projects

Agrimix™ is a concrete specifically developed for agricultural applications. Whether it's for use on silaging platforms, cesspits, slurry storage areas or agricultural buildings, Agrimix™ will respond to your needs. Agrimix™ meets the requirements of the Guide technique d'entreposage des fumiers (Technical Guide to the Storage of Manure - including cesspit specifications) published by the Ministry of Sustainable Development, Environment and Parks. Agrimix™ also complies with the requirements of CSA A23.1-09, the Canadian standard for Class A-3 (30 MPa) or A-4 (25 MPa) concrete. These requirements have made it possible to produce concrete capable to withstand agriculture's aggressive chemical environments as well as the effects of freeze-thaw cycles.

### Placement

The placement of Agrimix™ uses conventional equipment, i.e.: pump, concrete bucket, or directly from the concrete mixer. If a pump is used, a pipe diameter of at least 100 mm with a 75 mm reducer is recommended.

### Curing

A seven-day water cure is essential to ensure that the material meets the demands of agricultural environments. This type of cure will yield a more impervious concrete with minimal shrinkage and optimal strength.

### Fluidity

Agrimix™ is a concrete whose slump can be adapted to the specific placement required for each job site. The use of the latest generation of admixtures makes it possible to deliver Agrimix™ with a nominal slump of 100 +/- 30 mm, which can be adjusted according to the client's specific needs, using a superplasticizer.

## Technical characteristic

Characteristics	Agrimix™
Slump	100 +/- 30 mm
Air content	5 to 8 %
Compressive strength at 24 hrs.	5 to 10 MPa
Compressive strength at 28 days	25 or 30 MPa
Water/cement ratio	< 0.55
Type of cement	GU or GUb
Aggregate size	20 or 14 mm





## WESTERN REGION



Administration / Sales  
300 Saulnier St.  
Laval (Québec) H7M 3T3  
Canada  
450 629-0100 • 1 800 361-2388  
Fax: 450 629-2175

### Orders

Montréal / Montréal-Est  
Laval / Rive-Nord / La Prairie / Vaudreuil-Dorion  
514 332-1901 • 1 800 561-7837  
Rive-Sud / Mont-Saint-Hilaire  
450 467-2864 • 1 800 483-2386



Administration / Sales / Orders  
110 Bélanger St.  
Châteauguay (Québec) J6J 4Z2  
Canada  
450 699-0880 • 514 397-0333  
Fax: 450 699-3474



Administration / Sales / Orders  
200 Louis-Hébert St.  
Mascouche (Québec) J7K 0R5  
Canada  
450 474-4147 • Fax: 450 474-0095

## EASTERN REGION



Administration / Sales / Orders  
3725 Saint-Henri St.  
Québec (Québec) G1E 2T4  
Canada  
418 667-2060 • Fax: 418 666-9793  
Québec  
418 667-2066 – concrete  
418 667-2067 – aggregates  
Sainte-Marie-de-Beauce  
418 387-6651  
Saint-Raphaël  
418 243-2109  
1 800 463-7016 – concrete  
418 243-2106 – aggregates  
Témiscouata-sur-le-lac (Cabano)  
418 854-0908



Administration / Sales / Orders  
222 Léon-Vachon Blvd.  
Saint-Lambert (Québec) G0S 2W0  
Canada  
418 889-5111 • 1 800 561-6476  
Fax: 418 889-5112  
Saint-Augustin  
Saint-Lambert  
Saint-Jean-Port-Joli

## CENTRAL REGION



Administration / Sales / Orders  
Trois-Rivières  
885 Berlinguet St.  
Trois-Rivières (Québec) G8T 8N9  
Canada  
819 376-2540 • Fax: 819 371-3163  
Shawinigan  
819 539-6921

